

# 2000 SERIES

## TECHNICAL DATA



PAL ADHESIVE  
PRODUCTS Ltd

Product datasheet Issue No 4 Issued Nov 2004

### RA 2320/2325 EURATRANS REINFORCED ACRYLIC TRANSFER TAPE

2320 on std. 76mm cores, 2325 on 25mm dispenser cores

#### TECHNICAL DETAILS

#### TYPICAL VALUE

#### UNITS

Thickness, adhesive + carrier	0.060	mm
Release liner thickness	0.055	mm
180 degree peel adhesion: Open side	700	N/m
Closed side	700	N/m
Polyester loop tack: Open side	500	N/m
Closed side	500	N/m
Liner release	10	N/m
Service temperature	-10 to +100	Deg. C.
pH of water extract	7.0 - 7.5 *	
Recommended application temperature	+5 to +25	Deg. C.
Shear adhesion, 1Kg @ 23 deg. C.	30	Hours
Shelf life	12	Months

Test Methods: BS 7116

\*Test Method BS EN 60454-2

THE ABOVE INFORMATION IS GIVEN IN GOOD FAITH AND FOR GUIDANCE ONLY.  
ALL DATA IS BASED UPON AVERAGE VALUES. THE PURCHASER SHALL BE RESPONSIBLE FOR  
DETERMINING THE SUITABILITY OF THIS PRODUCT FOR HIS PURPOSES.



PAL ADHESIVE  
PRODUCTS Ltd

Darlaston Road Ind. Estate, Darlaston Road, Wednesbury, WS10 7TN UK.  
Email: sales@paladhesives.co.uk  
Tel: +44 (0)121 - 526 5151

Fax: +44(0)121- 568 6797