

# 2000 SERIES

## TECHNICAL DATA



PAL ADHESIVE  
PRODUCTS Ltd

Issue number 1

Issued October 2004

### RA 2335 REINFORCED PERM/PEEL ARCYLIC TRANSFER ADHESIVE

#### TECHNICAL DETAILS

#### TYPICAL VALUE

#### UNITS

Thickness, adhesive plus carrier		0.060	mm
Thickness, release liner		0.065	mm
Peel adhesion to steel:	Open side	500	N/m
	Liner side	160	N/m
Polyester loop tack:	Open side	600	N/m
	Liner side	240	N/m
Static shear adhesion,	1Kg at 23 Deg.C	30	Hours
Liner release		10	N/m
Service temperature range		-10 to +100	Deg. C
Recommended application temperature range		+5 to +25	Deg. C
Shelf life		12	Months

Test Methods: BS 7116

THE ABOVE INFORMATION IS GIVEN IN GOOD FAITH AND FOR GUIDANCE ONLY.  
ALL DATA IS BASED UPON AVERAGE VALUES. THE PURCHASER SHALL BE RESPONSIBLE FOR  
DETERMINING THE SUITABILITY OF THIS PRODUCT FOR HIS PURPOSES.



PAL ADHESIVE  
PRODUCTS Ltd

Darlaston Road Ind. Estate, Darlaston Road, Wednesbury, WS10 7TN UK.

Email: [sales@paladhesives.co.uk](mailto:sales@paladhesives.co.uk)

Tel: +44 (0)121 - 526 5151

Fax: +44(0)121- 568 6797